

Daraclean® 282



 QUEBEC
 ONTARIO

 164, St-Jean-Baptiste Mercier, QC J6R 2C2
 275, Sheldon D Cambridge, ON 519-894-9069

 450-691-9090
 519-894-9069
 ALBERTA
7307, 50 street NW
Edmonton, AB T6B 2J9
587-689-6811
Ifields@qnde.ca

ww.gnde.ca

-800-361-3630

Alkaline Aqueous Cleaner

A low-foaming, all-purpose alkaline cleaning solution, Daraclean® 282 is an excellent cleaner for a broad spectrum of soils.

This multi-purpose industrial cleaner has excellent soil-rejecting properties and suspends soils until they settle and can be removed by filtering or skimming, for a cleaning bath which lasts much longer than other water-based cleaners.



Daraclean 282 can be used in concentrations up to 25 percent (20 percent for CARB compliance) in immersion, ultrasonic, spray and steam applications.

Moderately alkaline, with low foam levels, Daraclean 282 contains inhibitors to prevent metal corrosion, and has no phosphates and is hard water tolerant.

Daraclean 282 meets all major aerospace specifications for NDT cleaning, is safe to use on most metals and is non-aggressive on aluminum, magnesium and titanium alloys.

BENEFITS

Maximize range of use

- Effectively cleans a wide variety of soils and contaminates from parts
- Approved for NDT pre-cleaning due to low silicates and low residue
- Conforms to all major aerospace requirements
- Works with most application methods and equipment for increased flexibility
- Added corrosion inhibitors protect parts and equipment against rust

Maximize operator comfort and safety

- Promotes better inspection quality by providing the operator with a more comfortable work environment
- Reduces discomfort from strong odors
- Exceeds all EHS requirements

FEATURES

- Multi-purpose alkaline cleaner
- Low foam level
- Aerospace compliant
- Works on a wide range of materials
- Cleans a broad spectrum of soils
- Multi-metal safe
- Low silicates
- Low residue





APPLICATIONS

Cleaning methods:

- Dipping / immersion cleaning
- Ultrasonic cleaning
- Spray cleaning
- Steam cleaning

Ideal for:

- Aluminum
- Anodized aluminum
- Brass and bronze
- Carbon steel
- Cast iron
- Stainless steel
- Copper
- Magnesium
- Nickel
- Superalloys
- Plated metals
- Titanium

Removes:

- Buffing compounds
- Carbonized soils
- Cutting fluids
- Heavy oils and dirt
- Lubricant oils
- Machine oils
- Machining fluid
- Medium weight and lube oil
- Motor oil
- Synthetic coolant
- Water-soluble oils

Applications:

Excellent	••••			s & Bronze	on Steel & Iron	oer.	Magnesium	Nickel & Superalloys	ing Cr, Ir, Pt)	Stainless Steel	mni	
Good	•••											
Fair	••	Aluminum	Anodized Aluminum									
Poor	•											
Not Recommended			Alum	Anoc	Brass	Carbon S Cast Iron	Copper	Magı	Nickel & Superall	Platting (Cd, Cr,	Stain	Titanium
Water-Soluble Oils		••••	••••	••••	••••	••••	•••	••••	••••	••••	•••	
Machining Fluid		••••	••••	••••	••••	••••	•••	••••	••••	••••	•••	
Synthetic Coolants		••••	••••	••••	••••	••••	•••	••••	••••	••••	•••	
Medium Weight Oils		••••	••••	••••	••••	••••	•••	••••	••••	••••	•••	
Lube Oils		••••	••••	••••	••••	••••	•••	••••	••••	••••	•••	
Buffing Compounds		••••	••••	••••	••••	••••	•••	••••	••••	••••	•••	
Motor Oils		••••	••••	••••	••••	••••	•••	••••	••••	••••	•••	
Heavy Petroleum Oils		••••	••••	••••	••••	••••	•••	••••	••••	••••	•••	
Carbonized Soils		•••	•••	•••	•••	•••	••	•••	•••	•••	••	
Railroad & Axel Grease												
Glues												
Spray Adhesives												





SPECIFICATION COMPLIANCE

- AMS 1551, 1551A
- ARP 1512
- ASTM F945, F519 TYPE 1 C
- BAC 5763
- Boeing D6-48809
- CSS 253
- GEAE Method 22, 51145
- Honeywell ARP 4992
- Pratt and Whitney PMC 1429
- PWA 36604
- PWA K231
- RR CSS 204 Type A

PROPERTIES

pH Level	Alkaline					
Foam Level	Low					
Silicates	Yes					
Phosphates	No					
Hard Water Tolerance	Moderate					
Aerospace Compliant	Yes					
SCAQMD Certified	No					

USE RECOMMENDATIONS

Cleaning Method	Concentration	Temp.	Typical Duration		
Immersion	3–25%	80 to 180°F / 27 to 82°C	2-30 mins		
Ultrasonic	3–25%	80 to 180°F / 27 to 82°C	2-30 mins		
Spray	1–12% Recomm.: 2–5%	130 to 180°F / 54 to 82°C	0.25–3 mins		
Steam	1–12%	150 to 200°F / 66 to 93°C	1–5 mins		

Storage temperature: 50 to 86°F / 10 to 30°C

PACKAGING

5 gal / 18.9 L pail 01-6000-40 NSN 6850-01-364-8328

55 gal / 208 L drum 01-6000-45 NSN 6850-01-364-8329

INSTRUCTIONS FOR USE

Dilute cleaner with water to the appropriate concentration or use. Cleaning efficiency can be improved with agitation and heat. Increasing cleaning bath temperature will decrease foaming.

Maintenance Recommendations

Maintain cleaning bath by skimming and/or filtering. Check in-use cleaner concentration to maintain cleaning effectiveness. The recommended method for measuring concentration is titration method.

Concentration Verification: HACH Alkalinity Titration Kit*

Titrant	0.5N Sulfuric Acid						
Indicator	Bromcresol Green-Methyl Red						
Concentration %	Titrant drops x 1.7						

^{*} Ordering info: Alkalinity Test Kit, Model AL-TA; Product # 2314500; Mfr. Hach Company; Website www.hach.com

HEALTH AND SAFETY

Review all relevant health and safety information before using this product. For complete health and safety information, refer to the product Safety Data Sheet, which is available at **www.qnde.ca**.

QUEBEC 164, St-Jean-Baptiste Mercier, QC J6R 2C2 T:(450)691-9090

ONTARIO 275 Sheldon Drive, Unit 3 Cambridge, ON N1T 1A3 T:(519) 894-9069

www.qnde.ca



Daraclean Compatibility with Plastics and Elastomers

Aqueous cleaners are known to have adverse effects on some gasket materials while having no effect on others. Adverse effects may include swelling and plasticising (softening) or swelling and disintegration (brittleness). The following lists Daraclean compatibility with a variety of elastomers when tested at 45°C for 92 days.

DARACLEAN		200	212	235	236	259	282	282GF	283
Flourinated Elastomer	Viton	Е	Е	Е	Е	Е	Е	Е	Е
Fluorinated Elastomer	PVDF	Е	Е	Е	Е	E	Е	Е	Е
Flourinated Elastomer	Teflon®	Е	Е	Е	Е	Е	Е	Е	Е
Fluorinated Elastomer	Kalrez®	Е	Е	Е	Е	Е	Е	Е	Е
Composite	Ceramics	Е	Е	Е	Е	Е	Е	Е	Е
Composite	Nickel Graphite	Е	Е	Е	Е	Е	Е	Е	E
Fiber	Nylon	Е	Е	Е	Е	Е	Е	Е	Е
Chloroprene	Neoprene	G	G	G	G	G	G	G	G
Polyvinyl Chloride	PVC	Е	Е	Е	Е	Е	Е	Е	Е
Isobutylene Isoprene	Butyl	G	G	G	G	G	G	G	G
Ethylene Propylene	E P Rubber	G	G	G	G	G	G	G	G
Polysulfide	Thiokol	G	G	G	G	G	G	G	G
Chlorosulfonated PE	Hypolon	G	G	G	G	G	G	G	G
Chloro Polyvinyl Chloride	CPVC	G	G	G	G	G	G	G	G
Polypropylene	Polypropylene	G	G	G	G	G	G	G	G
E P Diene Monomer	EPDM	G	G	G	G	G	G	G	G
Polyisoprene	Latex (Natural) Rubber	F	F	F	F	F	F	F	F
Syn. Polyisoprene	Latex(Synthetic)Rubber	F	F	F	F	F	F	F	F
Polyester/Polyether	(Poly)Urethane	F	F	F	F	F	F	F	F
Poly Methyl Methacrylate	Plexiglass	F	F	F	F	F	F	F	F
Styrene Butadiene	Buna-S	F	F	F	F	F	F	F	F
Styrene Nitrile Copolymer	Buna-N	F	F	F	F	F	F	F	F

Code:

E = Excellent, No effect. G = Good. Little or no effect F = Fair. Slight swelling, softening or brittleness. Switch to an alternate elastomer if possible.

P = Poor. Swelling, softness or brittleness noted. Not recommended for use with Daraclean.

Revised: January 2018

