

# ZP-4D

DISTRIBUÉ PAR / DISTRIBUTED BY:


**QUEBEC**

164, St-Jean-Baptiste  
Mercier, QC J6R 2C2  
450-691-9090  
info@qnde.ca

**ONTARIO**

275, Sheldon Drive, Unit 3  
Cambridge, ON N1T 1A3  
519-894-9069  
nadams@qnde.ca

**ALBERTA**

7307, 50 street NW  
Edmonton, AB T6B 2J9  
587-689-6811  
lfields@qnde.ca


www.qnde.ca

1-800-361-3630

## Dry Powder Developer

ZP-4D is a noncombustible, dry powder, Form a developer that is ideal for highly sensitive fluorescent penetrant processes. ZP-4D is applied to oven dried parts following the use of penetrants and forms a thin film on parts that enhances the visibility of ultra-fine discontinuities.

ZP-4D is listed on the QPL SAE AMS 2644 Qualified Product List and is approved for use by Pratt & Whitney.



### BENEFITS

- Even, thin developer coverage
- Enhances visibility of ultra-fine discontinuities
- Non-combustible powder

### SPECIFICATION COMPLIANCE

- AECL
- AMS 2644
- AMS 2647
- ASME
- ASTM E1417
- ASTM E165
- Boeing BAC 5423 PSD 6-46 or 8-4
- Boeing PS-21202
- GE P3TF2
- Honeywell EMS 52309
- ISO 3452-2
- MIL-STD-2132
- MIL-STD-271
- Pratt & Whitney 4356
- QPL SAE AMS 2644

### APPLICATIONS

**Defect location:** open to surface

**Ideal for:**

- Castings
- Welds and forgings
- Turbine components
- Critical components

**Defect examples:**

- Cracks
- Seams
- Porosity

### USE RECOMMENDATIONS

<b>NDT Method</b>	Fluorescent Penetrant Testing (Type 1)
<b>Form(s)</b>	a
<b>Type 1 Penetrant Methods</b>	A, B, C, and D
<b>Usage Temperature</b>	40 to 125°F / 5 to 52°C
<b>Storage Temperature</b>	50 to 86°F / 10 to 30°C
<b>Required Equipment</b>	UV light source

## PROPERTIES

Particle Size	< 30 µm
Density	15 lb./ft. <sup>3</sup> (240 kg/m <sup>3</sup> )
NPE-Free	Yes

## INSTRUCTIONS FOR USE

ZP-4D may be applied by dusting, spraying, or dipping. Dipping is the least preferred method of application as some indication scrubbing can result and developer can become contaminated quickly with penetrant. Electrostatic spray application is possible, but care is required to prevent excessive developer build-up which will mask indications. For best results, allow a minimum of ten minutes for developing time before inspecting.

## PACKAGING

Packaging	Country of Origin	Part Number
10 lb / 4.53 Kg	USA	01-3330-69
20 lb / 9.07 kg		01-3330-75
5 kg tub	UK	055C084

## HEALTH AND SAFETY

Review all relevant health and safety information before using this product. For complete health and safety information, refer to the product Safety Data Sheet.

DISTRIBUÉ PAR / DISTRIBUTED BY:

**QUEBEC**164, St-Jean-Baptiste  
Mercier, QC J6R 2C2  
450-691-9090  
info@qnde.ca**ONTARIO**275, Sheldon Drive, Unit 3  
Cambridge, ON N1T 1A3  
519-894-9069  
nadams@qnde.ca**ALBERTA**7307, 50 street NW  
Edmonton, AB T6B 2J9  
587-689-6811  
lfields@qnde.ca[www.qnde.ca](http://www.qnde.ca)

1-800-361-3630